

VII.III. MATERIALI ZAŠČITNIH CEVI PO NORMAH

W.Nr.	DIN	AISI	UNS	SS	AFNOR/NF	BS	EN
1,4000	X 6 Cr 13	410 S	S 40500	2301	Z 8 C 12	403 S 17	1,4000
1,4005	X 12 CrS 13	416	S 41600	2380	Z 11 CF 13	416 S 21	1,4005
1,4006	X 10 Cr 13	410	S 41000	2302	Z 10 C 13	410 S 21	1,4006
1,4016	X 6 Cr 17	430	S 43000	2320	Z 8 C 17	430 S 15	1,4016
1,4021	X 20 Cr 13	420	S 42000	2303	Z 20 C 13	420 S 37	1,4021
1,4028	X 30 Cr 13	420 F	S 42000	2304	Z 33 C 13	420 S 45	1,4028
1,4034	X 46 Cr 13	--	--	2304	Z 44 C 14	420 S 45	1,4034
1,4057	X 17 CrNi 16-2	431	S 43100	2321	Z 15 CN 16.02	431 S 29	1,4057
1,4104	X 14 CrMoS 17	430 F	S 43020	2383	Z13 CF 17	---	1,4104
1,4112	X 90 CrMoV 18	440 B	S 44003				1,4112
1,4122	X 39 CrMo 17-1						1,4122
1,4301	X 5 CrNi 18-10	304, 304 H	S 30400	2332	Z 6 CN 18-09	304 S 15	1,4301
1,4303	X 4 CrNi 18-12	305	S 30500		Z 5 CN 18-11 FF	305 S 19	1,4303
1,4305	X 10 CrNiS 18-9	303	S 30300	2346	Z8 CNF 18-09	303 S 31	1,4305
1,4306	X 2 CrNi 19-11	304 L	S 30403	2352	Z 3 CN 19-11	304 S 11	1,4306
1,4310	X 2 CrNiN 18-8	301	S 30100	2331	Z 11 CN 18-08	301 S 22	1,4310
1,4311	X 2 CrNiN 18-10	304 LN	S 30452	2371	Z 3 CN 18-10 Az		1,4311
1,4362	X 2 CrNiN 23-4			2327	Z 3 CN 23-04 Az		1,4362
1,4401	X 5 CrNiMo 17-12-2	316	S 31600	2347	Z 7 CND 17-11-02	316 S 31	1,4401
1,4404	X 2 CrNiMo 17-12-2	316 L	S 31603	2348	Z 3 CND 18-11-02	316 S 11	1,4404
1,4406	X 2 CrNiMoN 17-11-2	316 LN	S 31651		Z 3 CND 17-11 Az	316 S 61	1,4406
1,4417	X 26 NiMoSi 19-5		S 31500	2376			1,4417
1,4418	X 4 CrNiMo 16-5-1			2387	Z 6 CND 16-05-01		1,4418
1,4429	X 2 CrNiMoN 17-13-3	316 LN	S 31651	2375	Z 3 CND 17-12 Az	316 S 36	1,4429
1,4435	X 2 CrNiMo 18-14-3	316 L	S 31603	2353	Z 3 CND 18-14-03	316 S 11	1,4435
1,4436	X 3 CrNiMo 17-13-3	316	S 31603	2343	Z 3 CND 18-12-03	316 S 11	1,4436
1,4438	X 2 CrNiMo 18-15-4	317	S 31703	2367	Z 3 CND 19-15-04	317 S 12	1,4438
1,4439	X 2 CrNiMoN 17-13-5	317 LN					1,4439
1,4449	X 5 CrNiMo 17-13	317	S 31700			317 S 16	1,4449
1,4460	X 3 CrNiMoN 27-5-2	329	S 32900	2324	Z 5 CND 27-05 Az		1,4460
1,4462	X 2 CrNiMoN 22-5-3	--	S 31803	2377	Z 3 CND 22-05 Az	318 S 13	1,4462
1,4512	X 6 CrTi 12	409	S 40900	--	Z 3 CT 12	409 S 19	1,4512
1,4539	X 1 NiCrMoCuN 25-20-5		N 08904	2562	Z 2 NCDU 25-20	904 S 13	1,4539
1,4541	X 6 CrNiTi 18-10	321	S 32100	2337	Z 6 CNT 18-10	321 S 31	1,4541
1,4550	X 6 CrNiNb 18-10	347, 348	S 34700	2338	Z 6 CNNB 18-10	347 S 31	1,4550
1,4570	X 6 CrNiCuS 18-9 2						1,4570
1,4571	X 6 CrNiMoTi 17-12-2	316 TI	S 31635	2350	Z 6 CNDT 17-12	320 S 31	1,4571
1,4713	X 10 CrAl 7				Z 8 CA 7		1,4713
1,4724	X 10 CrAl 13	405	S 40500		Z 10 C 13	405 S 17	1,4724
1,4742	X 10 CrAl 18				Z 12 CAS 18		1,4742
1,4762	X 10 CrAl 24	446	S 44600	2322	Z 12 CAS 25		1,4762
1,4821	X 20 CrNiSi 25-4	327		2323	Z 20 CNS 25.04		1,4821
1,4828	X 15 CrNiSi 20-12	309	S 30900		Z 17 CNS 20-12	309 S 24	1,4828
1,4833	X 7 CrNi 23-14	309 S	S 30908		Z 15 CN 23 13		1,4833
1,4835	X 9 CrNiSiNCE 21-11-2	-	-	2368	-		1,4835
1,4841	X 15 CrNiSi 25-21	314, 310	S 31400		Z 15 CNS 25-20	314 S 25	1,4841
1,4845	X 12 CrNi 25-21	310 S	S 31008	2361	Z 12 CN 25.20	310 S 31	1,4845
1,4864	X 12 NiCrSi 36-16	330	N 08330		Z 20 NCS 33-16	3076NA17	1,4864
1,4876	X 10 NiCrAlTi 32-20	B 163			Z 8 NC 33-21	3076Na15h	1,4876
1,4878	X 18 CrNiTi 18-10	321	S 32100	2337	Z 6 CNT 18-10	321 S 51	1,4878
1,4891	X 4 CrNiSiN 18-10	153 MA*	S 30815	2368			1,4891
1,4893	X 8 CrNiSiN 21-11	253 MA*					1,4893
1,4547	X 2 CrNiMoNCu 20-18-6	254 SMO*	S 31254	2378			1,4547
1,4410	X 2 WniMoN 25-7-4	SAF 2507*	S 32750	2328			1,4410

W.Nr.	- številka jekla	UNS	- unificiran institut	BS	- britanski standard
DIN	- nemški institut	SS	- svenski	EN	- evronorm
AISI	- ameriški institut	FNOR/NF	- francoski institut		